

JIS規格 (JIS G 3323)

めっきの付着量

付着量記号 (日新規格 1)	両面3点平均 最小付着量 (g/m ²)	両面1点 最小付着量 (g/m ²)
K06	60	51
K08	80	68
K10	100	85
K12	120	102
K14	140	119
K18	180	153
K20	200	170
K22	220	187
K25	250	213
K27	275	234
K30	300	255
K35	350	298
K45	450	383

付着量記号 (日新規格 2)	両面3点平均 最小付着量 (g/m ²)	両面1点 最小付着量 (g/m ²)
45	70	60
60	90	77
-	-	-
-	-	-
90	140	119
120	190	162
-	-	-
150	230	196
-	-	-
190	290	247
-	-	-
300	500	425